

25 6. A method according to claim 5, wherein in the
ultrasonic washing step, ultrasonic washing with a wash
solution containing a surface-active agent and

ultrasonic washing with pure water are performed in succession.

5 7. A method according to claim 6, wherein the deterioration layer removing stage further includes a step of rinsing the substrate with pure water and a step of drying the rinsed substrate after the surface of the substrate is ultrasonic-washed with pure water.

10 8. A method according to claim 1, wherein the contamination removing stage includes the steps of:
immersing the substrate in acetone;
taking out the substrate from the acetone and then wiping the surface thereof with a paper containing
15 diamond powder;
processing the wiped surface of the substrate with solvent; and
processing the surface-processed substrate with UV/O3.

20 9. A method according to claim 8, wherein the solvent is ether.

25 10. A method according to claim 6, wherein the surface-active agent is an alkalescent surface-active agent.

11. A method according to claim 7, wherein the drying step is performed with a warm air.

12. A method according to claim 1, wherein the
5 machining stage includes a step of cutting the substrate from a CaF₂ single crystalline base substrate and polishing the surface of the cut substrate with a predetermined surface shape.

10 13. A method according to claim 12, wherein the machining stage includes a step of forming a protective film on the polished surface of the substrate, and the contamination removing stage is performed after the protective film is removed from the surface of the
15 substrate.

14. A method according to claim 1, wherein the contamination is one of abrasive, oil content, and other foreign matter.
20

15. A method according to claim 1, wherein a surface roughness of the optical element is 0.5 to 0.55 nm by an examination with an RMS.

25 16. A method according to claim 1, wherein the optical element is one of a lens, a prism, a transparent plate, and a transparent rod.

5

removing a deterioration layer in the surface of the substrate after the machining.

10

an optical system having an optical element
manufactured by the manufacturing method according to
any one of claims 1 to 17, for illuminating a wafer
with laser light having a wavelength of 200 nm or less.

15

19. A device manufacturing method comprising the stages of: exposing the wafer by the exposure apparatus according to claim 18; and developing the exposed wafer.

20

20. An optical element washing machine including an optical element holding unit, an excimer laser unit, and a focal control unit for focusing excimer laser light from the excimer laser unit, the optical element holding unit having a holder, a rotation stage, and a three dimensional control stage,

25

in which the holder is means for holding an optical element,

the rotation stage is means for rotating the holder,

the three dimensional control stage is a constitution element of position control means for causing the rotation stage to move in a vertical direction and/or a horizontal direction,

5 the excimer laser unit is a light source for emitting ultraviolet radiation, and

10 the focal control unit has basic control value setting means for setting a basic control value for a focal matching state of the ultraviolet radiation from the excimer laser unit, focal matching determination means for determining a focal matching state of the excimer laser light, and correction means for sending a correction amount corresponding to a determination result of the focal matching determination means to the
15 position control means.

109090" 6666/860